



PRODUCT:

MULTICURE R

HYDROCARBON RESIN EMULSION CURING COMPOUND (Type 1-D, Class B)

Hydrocarbon Resin based curing compound conforming to AS 3799 and Hot Pour Asphalt suitable.

DESCRIPTION:

MULTICURE R is a liquid applied curing compound which consists of a processed blend of petroleum and resin based hydrocarbons. When applied at the recommended application rate MULTICURE R minimizes moisture loss in freshly laid concrete thus improving the curing of the concrete providing increased strength and durability and improved resistance to surface dusting.

USE:

Mainly used on freshly laid concrete floors, carparks, hardstand areas, warehouses, bridge ramparts etc. Also used for curing vertical concrete areas immediately after the stripping of forms to assist strength development, improve chemical resistance, etc.

ADVANTAGES OF USE:

- **Rapid film formation time**
- **Water resistant film formed**
- **Utilises low VOC formula**
- **Complies with GREEN STAR- OFFICE DESIGN V3 IEQ-13**
- **Economical, ease of application reduces labour cost**
- **Eliminates the need for damp hessian, sand or polythene**
- **Enables concrete to hydrate more efficiently**
- **Increases concrete strength and dusting resistance**
- **Reduces surface shrinkage and cracking**
- **Odourless when dry**

STANDARDS COMPLIANCE

MULTICURE R conforms to AS 3799-1998: liquid membrane forming curing compounds for concrete, having a Moisture Retention Efficiency of 93%. Test certificates are available on request.

MULTICURE R conforms to R.T.A. specification R82, R83, R84. & is listed on QDMR as an approved product.

MULTICURE R is also available in pigmented variants of white (Type 2- Class B) & black (Type 3- Class B). Test certificates will be available shortly. These products are usually specified when temperature conditions dictate viz. during the period November- April (white) and winter for black, to assist in the optimizing of temperature conditions for concrete curing.

**DESIGN & SPECIFICATION
DETAIL**

The coating should be applied in a single coat at the specified rate of 5m/L (0.2L/m²) to achieve a total dry film thickness to achieve the correct curing properties. MULTICURE R **must** be applied on to the substrate at the coverage rates recommended as a minimum specification. If specified at higher rates then allowance for removal of resulting film must be made allowed for before additional works.

CONCRETE CURING COMPOUND

All designated areas are to have a liquid curing compound applied to the freshly finished concrete. The curing compound will be a hydrocarbon resin emulsion, complying with AS3799. Such a material is MULTICURE R as supplied by Chemical House. The curing compound is to be applied in accordance with the manufacturers application instructions.

DIRECTIONS FOR USE :

MULTICURE R should be evenly sprayed over the freshly laid concrete as soon as possible after final trowelling. Ideally MULTICURE R should be applied as soon as the surface bleed water has evaporated.

LIMITATIONS:

Certain adhesives for vinyl tiles, or other types of resilient flooring, and paints of an approved grade may be applied to concrete coated with MULTICURE R. It is important however that the concrete should be thoroughly cured prior to such application, and that a test area has been completed for approval. Cement based renders and toppings should not be applied over MULTICURE R. First remove the MULTICURE R by stripping with STRIPSEAL, EASI-ORANGE or sand blasting or



RFA (AUSTRALIA) PTY LTD

ABN 31 010 583 721 ACN 010 583 721

P.O. BOX 45 LUTWYCHE
QUEENSLAND AUSTRALIA 4030

scabbling to provide a mechanical key. The life of MULTICURE R will depend on the weather exposure conditions to which it has been subjected; the coating is designed to break down with weathering. Continual exposure to UV light and weather of at least 12 weeks is suggested to facilitate this process. The bond of MULTICURE R is likely to fail if the product is applied to concrete or masonry substrates subject to back water pressure, and/or where extraneous salt particles are carried from the substrate to the interface by vapour or condensation.

A clear appearance with slight yellow cast is obtained. MULTICURE R will oxidize and breakdown when subject to ultra-violet radiation from sunlight.

COVERAGE:

5 m² per litre (0.2L/m²)

CLEAN UP:

MULTICURE R should be removed from tools and equipment with water if still wet and Solvent 100, Easi-Orange or StripSeal formulated strippers from Chemical House, if the dry film has formed.

STORAGE:

Store in cool, dry conditions, away from sources of heat and naked flames, in original, unopened packs. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced.

PACKS:

20L, 200L, 1000L

DISCLAIMER:

This Product Data Sheet (PDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this PDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. RFA or any related entities does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

Ref:Multicure_R_May2013_pds.doc

Date: May 2013